

Mannington MR-725 is a two-component urethane adhesive designed for use with various floor covering materials on most smooth, solid surfaces. When parts A and B are thoroughly mixed together, they form a reactive adhesive that cures to a tough, flexible film with good adhesion to a wide range of materials.

TECHNICAL DATA

	A	B	MIX
Base:	Urethane	Polyamide	Urethane
Color:	White	Black	Grey
Viscosity:	60,000 cps	700 cps	50,000 cps
Wt./Gal.:	12.0 lbs	8.2 lbs	11.9 lbs
Mix Ratio:			
By Wt:	12.5	1.0	
By Vol:	8.63	1.0	
Flash Point:	>200°F	>200°F	>200°F
V.O.C., LBS./GAL:	<0.1	<0.1	<0.1
G/L:	<12	<12	<12
% Solids, Wt:	>99	>99	>99
Shelf Life:	6 months	6 months	

POT LIFE

Mannington MR-725 has a 45 - 60 minute pot life at 75°F, when parts A and B are thoroughly mixed. Pot life will be shorter at higher temperatures. Part A and B must be mixed thoroughly.

SET TIME

At 75°F, allow 6 - 8 hours for light foot traffic, 24 hours for heavy foot traffic. Set time will be longer at lower temperatures. Allow 72 hours for heavy duty traffic.

OPEN TIME

The minimum open time is immediately after the adhesive is applied. The maximum open time is 45 - 60 minutes after the adhesive is applied, at 75°F. Higher temperatures will result in shorter open times.

SURFACE PREPARATION

Concrete must be clean and dry prior to adhesive application. Concrete must be free of curing membranes, paint, sealers or hardeners. Concrete must be at least 30 days old and have less than 5% moisture to a depth of one inch (or less than 3 lbs./1,000 sq. ft. per 24-hour period using the Rubber Manufacturers Association CaC1 test). Subfloor preparation must comply with ASTM F-710-82. Do not apply adhesive if surface temperature drops below the dew point. Do not apply adhesive if hydrostatic pressure exists.

OTHER

Do not apply when temperature will go below 50°F or when surface temperature is below the dew point. Ideal application temperature is 75° F.

COVERAGE

1/16 x 1/16 x 1/16 in. square notch trowel = 125 - 150 sq. ft. per gallon
 1/32 x 1/16 x 1/32 in. u-notch trowel = 225 - 250 sq. ft. per gallon.

CAUTION: READ MSDS THOROUGHLY BEFORE USING THIS PRODUCT.

Choices that Work.

Questions about warranties? call 800 241 2262 or visit www.manningtoncommercial.com

June, 2015